

The Concentration Dependence of the Size and Symmetry of a Bottlebrush Polymer in a Good Solvent

Daniel F. Sunday^{1*}, Alexandros Chremos,^{1*} Tyler B. Martin¹, Alice B. Chang², Adam B. Burns¹, Robert H. Grubbs²

1. Materials Science and Engineering Division, National Institute of Standards and Technology, Gaithersburg, MD 20899, United States
2. Division of Chemistry and Chemical Engineering, California Institute of Technology, Pasadena, CA 91125, United States

* Daniel.Sunday@nist.gov, Alexandros.Chremos@nist.gov

Supplemental Information

The general Guiner-Porod (GGP) model is described by Equations 1-3.¹ This model describes the scattering by using Guinier regions interconnected by power law regimes. Crossover points (Q_1 , Q_2) and scaling factors (G_1, G_2) are calculated to ensure self-consistency in the transition between different regions. The model uses shape factors (s_1, s_2) to describe the approximate shape of the scattering features, where 0 represents a sphere, 1 represents a cylinder or rod, and 2 represents lamellae. A background and intensity scaling term were also included in the model. The implementation of the general Guinier-Porod model in Sasview is available in the Sasview marketplace (<http://marketplace.sasview.org/>), with the model name “2 Layer General Guinier Porod”. The hard sphere structure factor was used where appropriate and its implementation is described in the sasview documentation.

$$I(Q) = \frac{G_2}{Q^{s_2}} \exp\left(-\frac{Q^2 R_{g,2}^2}{3-s_2}\right) \text{ for } Q \leq Q_2 \quad (1)$$

$$I(Q) = \frac{G_1}{Q^{s_1}} \exp\left(-\frac{Q^2 R_{g,1}^2}{3-s_1}\right) \text{ for } Q_2 \leq Q \leq Q_1 \quad (2)$$

$$I(Q) = \frac{D}{Q^d} \text{ for } Q \geq Q_1 \quad (3)$$

Table 1: Fit Results to GGP model (Figures 3 and 4). Uncertainties represent 95% confidence intervals as evaluated by the Monte-Carlo Markov Chain analysis performed by the Dream algorithm in Sasview.

Volume Fraction	$R_{g,2}$ (Å)	$R_{g,1}$ (Å)	R_g	s_1	s_2	l_p (Å)
0.0870	39.8 ± 0.1	27.3 ± 0.1	35.0 ± 0.9	0.74 ± 0.13	0	7.9 ± 0.1
0.0792	39.0 ± 0.2	28.6 ± 0.1	35.5 ± 0.9	0.68 ± 0.15	0	7.7 ± 0.1
0.0739	38.3 ± 0.1	29.4 ± 0.1	35.8 ± 1.0	0.98 ± 0.18	0	7.4 ± 0.1
0.0578	40.5 ± 0.1	29.2 ± 0.1	36.6 ± 1.1	0.82 ± 0.12	0	8.2 ± 0.1
0.0504	41.7 ± 0.1	30.7 ± 0.1	38.0 ± 1.0	0.73 ± 0.15	0	8.8 ± 0.1
0.0424	41.6 ± 0.2	29.5 ± 0.1	37.2 ± 0.7	0.88 ± 0.16	0	8.7 ± 0.1
0.0350	45.8 ± 0.1	32.2 ± 0.1	40.8 ± 1.4	0.9 ± 0.18	0	10.7 ± 0.1
0.0287	47.5 ± 0.2	30.0 ± 0.1	40.3 ± 1.7	0.8 ± 0.33	0	11.5 ± 0.1
0.0232	53.2 ± 0.4	35.5 ± 0.1	46.3 ± 0.2	0.64 ± 0.08	0	14.7 ± 0.1
0.0196	60.3 ± 0.3	36.4 ± 0.1	50.1 ± 0.2	0.61 ± 0.05	0	19.3 ± 0.1
0.0165	66.4 ± 0.1	29.5 ± 0.1	49.6 ± 0.2	1.01 ± 0.08	0	23.9 ± 0.1
0.0124	77.2 ± 0.3	28.6 ± 0.1	55.2 ± 0.2	1.1 ± 0.09	0	33.8 ± 0.2
0.0085	82.9 ± 0.8	26.0 ± 0.1	57.3 ± 0.4	1.25 ± 0.10	0.1 ± 0.01	40 ± 0.4
0.0074	84.1 ± 1.5	25.9 ± 0.1	58.0 ± 0.9	1.24 ± 0.11	0.2 ± 0.02	41.6 ± 0.8
0.0043	89.0 ± 1.2	25.8 ± 0.1	60.8 ± 0.6	1.3 ± 0.03	0.1 ± 0.01	47.9 ± 0.7
0.0021	96.2 ± 1.4	22.5 ± 0.1	64.1 ± 0.7	1.47 ± 0.04	0.1 ± 0.02	58.5 ± 0.8
0.0010	99.5 ± 4.0	22.5 ± 0.1	66.0 ± 2	1.37 ± 0.06	0.1 ± 0.05	65.7 ± 2.7

References

- (1) Hammouda, B. A New Guinier–Porod Model. *J. Appl. Crystallogr.* **2010**, *43* (4), 716–719.
<https://doi.org/10.1107/S0021889810015773>.