

Acta Crystallographica Section B

**Structural
Science**

ISSN 0108-7681

Structure and thermal behavior of the new superprotonic conductor $\text{Cs}_2(\text{HSO}_4)(\text{H}_2\text{PO}_4)$. Erratum

Calum R. I. Chisholm and Sossina M. Haile

Copyright © International Union of Crystallography

Author(s) of this paper may load this reprint on their own web site provided that this cover page is retained. Republication of this article or its storage in electronic databases or the like is not permitted without prior permission in writing from the IUCr.

Structure and thermal behavior of the new superprotonic conductor $\text{Cs}_2(\text{HSO}_4)(\text{H}_2\text{PO}_4)$. Erratum

Calum R. I. Chisholm and Sossina M. Haile*

Materials Science 138-78, California Institute of Technology, Pasadena, CA 91125, USA

Table 2 in the paper by Chisholm & Haile [(1999), *Acta Cryst.* **B55**, 937–946] was printed incorrectly. The following is the correct version, including H-atom coordinates.

Table 2

Atomic coordinates and equivalent isotropic displacement parameters (\AA^2) for $\text{Cs}_2(\text{HSO}_4)(\text{H}_2\text{PO}_4)$.

$$U_{\text{eq}} = (1/3)\sum_i \sum_j U^{ij} a^i a^j \mathbf{a}_i \cdot \mathbf{a}_j.$$

	x	y	z	U_{eq}
Cs(1)	0.7280 (1)	0.1588 (1)	0.1180 (1)	0.031 (1)
S/P†	0.7565 (1)	0.1621 (1)	−0.3887 (1)	0.022 (1)
O(1)	0.6584 (4)	0.0269 (3)	0.4937 (4)	0.032 (1)
O(2)	0.8377 (2)	0.2882 (2)	−0.4882 (3)	0.034 (1)
O(3)	0.6287 (2)	0.2447 (2)	−0.2880 (2)	0.033 (1)
O(4)	0.8930 (2)	0.0690 (3)	−0.2607 (2)	0.039 (1)
H(1)‡	0.5387 (4)	0.0329 (6)	0.5012 (6)	0.080
H(2)§	0.8558 (2)	−0.0469 (3)	−0.2449 (2)	0.080

† Fixed site occupancy of 0.5S and 0.5P. ‡ Fixed site occupancy of 0.5. § Probable neighboring interstitial site at 0.6482, 0.3470 and −0.2775.

References

Chisholm, C. R. I. & Haile, S. M. (1999). *Acta Cryst.* **B55**, 937–946.